



CERAMI-TECH E.G.

Two Component Ceramic Epoxy Repair Compound



Thortex Cerami-Tech E.G. is a high performance multi purpose metal repair compound specifically developed for rebuilding metal components in a fluid flow environment damaged by erosion and corrosion.

The **Thortex Cerami-Tech E.G.** formulation uses a complex blend of epoxy resins and a polyamino-amide curing system reinforced with carbide and ceramic particles to produce a coating with a high level of abrasion and erosion resistance combined with optimum physical and mechanical strength.

Thortex Cerami-Tech E.G. can be applied to any damaged component in one easy application and is ideal for rebuilding pump bodies, impellers, propellers, guide vanes, valves, tube sheets, water boxes, rudders, heat exchangers etc.

Before proceeding, please read the following information carefully to ensure that the correct application procedure is fully understood.

SURFACE PREPARATION

All dust and loose material should be scraped away. Oil and grease should be removed with **Thortex Universal Cleaner**. Surfaces should then be abrasive blast cleaned to a minimum Sa2½ BS7079 Part A1 : 1989 or equivalent with a blast profile of 3 mil corresponding to 'Medium' in BS7079 Part C3/ISO 8503/1. All loose abrasive dust and debris must be blown clear or vacuum cleaned away.

Equipment that has been salt impregnated due to service conditions should first be wet blasted then dry abrasive blasted and checked for presence of salts, this process should be repeated until the salts are removed.

Alternatively, surfaces should be warmed with a blow torch or similar to bring salts up to the surface. The surface should once again be blast cleaned. This procedure must be repeated until no further sweating of impregnated salt is evident.

On sections of repair which are not required to bond to the **Thortex Cerami-Tech E.G.** these surfaces should be treated with **Thortex Release Agent**.

MIXING

Thortex Cerami-Tech E.G. is a two component material comprising base and activator components which must be mixed together before use.

Transfer the entire contents of the base and activator containers onto a clean mixing board or other suitable surface. Alternatively measure three volumes of base component and one volume of activator onto a clean mixing surface. The two components should be thoroughly mixed until completely streak free.

The mixed material should be used within 25 minutes of mixing at 68°F. This time will be reduced at higher temperatures and extended at lower temperatures.

APPLICATION

Application should not be carried out at temperatures below 40°F nor when relative humidity exceeds 85% or when the surface to be repaired is less than 5°F above the dew point.

The mixed material should be pressed firmly onto the prepared area, care should be taken to avoid air entrapment on deeply pitted surfaces. Application should be carried out as soon as possible after surface preparation is complete, and certainly the same day, otherwise flash blasting will be necessary before application.

Where necessary **Thortex Reinforcement Tape** should be stippled into the mixed product and further material applied over

In areas where a second layer of **Thortex Cerami-Tech E.G** is required, this application must be carried out within the initial set time for the first layer, if this is not possible surfaces will require thorough abrasion or abrasive blasting prior to any subsequent material being applied.

Machining of **Thortex Cerami-Tech E.G** will cause excessive tool wear so care should be taken to finish the repair to the required size or dimensions. Formers treated with **Thortex Release Agent** can be used to minimize machining.

Once the **Thortex Cerami-Tech E.G.** has reached initial set the material can be separated from surfaces treated with **Thortex Release Agent**.

All equipment must be cleaned IMMEDIATELY after use with **Thortex Universal Cleaner** or equivalent.

Volume Capacity
25.4 cu ins per kilo

Detailed working recommendations are available from the Technical Center on request.

PHYSICAL CONSTANTS

Mixing Ratio	Base	Activator	
	3	1	By volume
	5	1	By weight

Appearance	Base	Grey Paste
	Activator	Light Grey Paste

Drying & Cure times at 68°F	Usable Life	25 minutes
	Initial Set	1 hours
	Machining Time	2 hours
	Full Mechanical	5 days

Volume Solids 100%

V.O.C. Nil

Shelf Life Use within 5 years of purchase. Store in original sealed containers at temperatures between 40°F and 86°F.

Food Contact Meets USDA requirements for incidental food contact. Meets FDA requirements CFR 21.175.300 for food contact.

PHYSICAL PROPERTIES

Compressive Strength ADTM D695	1055 kg per cm ² (15000psi)
Tensile Shear Adhesion ASTM D1002	175 kg per cm ² (2500psi) (Grit Blasted Steel)
Flexural Strength ASTM D790	700 kg per cm ² (10000psi)
Heat Distortion Temperature ASTM D648	194°F
Hardness (Rockwell R) ASTM D785	100
Abrasion Resistance ASTM D4060	0.06 ml per 1000 cycles - 1 kg load/CS17 Wheel
Nuclear Decontamination BS 4247 Part 1	Excellent

HEALTH AND SAFETY

As long as normal good practice is observed **Thortex Cerami-Tech E.G.** can be safely used.

Protective gloves should be worn during use.

A fully detailed **Material Safety Data Sheet** is either included with the material or is available on request.

PACKAGING

Supplied in 2kg packs.

The information provided in this Product Data Sheet is intended as a general guide only and should not be used for specification purposes. The information is given in good faith but we assume no responsibility for the use made of the product or this information because this is outside the control of the company. Users should determine the suitability of the product for their own particular purposes by their own tests.

FOR FURTHER INFORMATION PLEASE CONTACT



Thortex America, Inc.

12 Iron Bridge Drive • Collegeville, PA 19426

Tel: 610 831 0222 • Fax: 610 831 1910

E-mail: info@thortex.com

www.thortex.com